



POR-15 POW-R-LINER

Application Information

PRODUCT DESCRIPTION

POR-15 POW-R-Liner is a coating system designed for applying to the rear bed of pick up trucks and other metal surfaces. The high performance urethane formulation cures quickly and provides superior UV protection and resistance to abrasion and chemicals.

Before you begin: Please use latex gloves during application and make sure that POW-R-Liner is applied in a well ventilated area.

Kit Contents:

4 Quarts POW-R-Liner Base
1 Container Hardener/Activator

What you Need to Start:

Spray Gun
Latex Gloves
Air Compressor
High quality masking tape

SURFACE PREPARATION

POR-15 POW-R-Liner can be applied to most original automotive manufacturers finishes, other metal surfaces and concrete.

For Metal Surfaces:

1. Surface should be lightly scuffed with a Scotch-Brite red pad or 80-120 grit sandpaper to ensure proper adhesion.
2. Loose paint and/or rust should be removed with a wire brush.
3. Dirt and dust needs to be removed with a water based degreaser...for best results use **POR-15 Marine Clean** and thoroughly rinse with tap water afterwards. Surface must be completely dry before taping and applying **POR-15 POW-R-Liner**.
4. Carefully mask off all areas that you wish not to be coated as well as latch bolt holes and fill drain plugs. All surrounding areas within reach of overspray must be taped off with a sufficient protective seal. This is critical to the overall success of the application.
5. For total rust protection, apply 1-2 coats of **POR-15 Rust Preventative Paint**. Follow the instructions for top-coating of **POR-15 Rust Preventative Paint**, prior to applying the **POR-15 POW-R-Liner**.

APPLICATION

1. Fill Can of POR-15 POW-R-Liner to the 'fill' line with POW-R-Liner Hardener/Activator.
2. Replace cap and shake strongly for two or three minutes.
3. POW-R-Liner can be applied using 30-70 PSI. Apply to surface with an even, sweeping motion to obtain the required texture. The lower the air pressure, the more texture the surface will have.
4. Additional coats can be applied in one hour. Not allowing an hour between coats, will slow overall cure times and impact quality of application.

Product Specifications

- Pot life at 20°C: approximately 60 minutes.
- Touch dry at 20°C: <1 hour subject to film thickness.
- Do not place heavy loads on the surface until POW-R-Liner is fully cured. For general use: 5-7 days at 20°C. For light duty: 2-3 days at 20°C.
- Approximate coverage: 125 square foot per Gallon.
- Do not use in extreme cold or hot temperatures. Ideal application temperature is 20°C, with humidity of less than 60%.

CAUTION: Use in well ventilated area. Wear gloves at all times.

KEEP OUT OF THE REACH OF CHILDREN.

The information set out in this flier is, so far as can be ascertained, true and accurate, but all recommendations are made without guarantee. Since the conditions of use of the Products sold by Permanent Painted Coatings Limited (New Zealand) ("PPC Limited") and Permanent Painted Coatings Pty Ltd (Australia) ("PPC Pty Ltd") are beyond the control of PPC Ltd and/or PPC Pty Ltd ("the Companies"), then the Companies to the full extent allowed by the law, disclaim any liability with respect to damage, injury or death consequent upon the use of the Products or consequent upon the use of the information contained herein. The Companies warrant that the Products supplied hereunder shall conform to the description or specification stated in this flier. The Companies make no warranties that Products supplied are made to certain industry specifications. To the full extent allowed by law, the liability of the Companies with respect to any breach of the aforesaid warranty shall be limited, at the option of the Companies, to payment of the cost of replacing the Products or of acquiring equivalent products and in no case shall the Companies be liable for consequential loss or damage. In no case will the Companies be liable to defend or pay award of damages assessed against the buyer in any suit or cause of action alleging that the use of the Products supplied hereunder infringe any patent. The Companies hereby expressly disclaim any written or unwritten, express or implied representation, warranty or condition against infringement of any patent with respect to such goods.



Permanent Painted Coatings

PERMANENT PAINTED COATINGS (2009) LTD

P O BOX 5614, Frankton, Hamilton 3242

Email: sales@por15.co.nz

Website: www.por15.co.nz